

AMENDMENTS TO THE SPECIFICATION

Please replace Table 1 on page 21, lines 1-19, with the following amended table:

Table 1

		Example 1	Example 2	Example 3	Comparative Example 1	Comparative Example 2	Comparative Example 3
Pressure sensitive adhesive composition	E-1	100					
	E-2		100				
	E-3			100			
	E-4				100		
	E-5					100	
	E-6						100
Tackifier resin		50	50	50	50	50	100
Curing agent ^{*2}		4	4	4	4	4	4
Toluene		-	-	-	-	50	-
Viscosity (Pa·s)		280.2	225.6	232.2	279.5	918.4	290.4
Adhesive strength (N/25mm)		30.6	25.4	26.8	7.6	10.2	9.8

*1: YS Polyester S-145 (product of YASUHARA CHEMICAL CO., LTD., terpene-phenol resin)

*2: Orgatix TC-100 (product of MATSUMOTO TRADING CO., LTD., titanium acetylacetonate)